

Technical data sheet Nylon

Ultimaker

Chemical Name	Polyamide
Description	Used by many manufacturers worldwide, Nylon is well-known for its impressive durability, high strength-to-weight ratio, flexibility, low friction, and corrosion resistance. Seamless 3D printing experience due to the reduced humidity absorption when compared to other Nylon filaments.
Key features	Industrial-grade impact and abrasion resistance, durable, high strength-to-weight ratio, low friction coefficient, and good corrosion resistance to alkalis and organic chemicals.
Applications	Functional prototyping, tooling and industrial modeling.
Non suitable for	Food contact and in-vivo applications. Applications where the printed part is exposed to temperatures higher than 80 °C

Filament specifications

	<u>Value</u>	<u>Method</u>
Diameter	2.85±0.05 mm	-
Max roundness deviation	0.05 mm	-
Net filament weight	750 g	-

Color information

<u>Color</u>	<u>Color code</u>
Nylon Transparent	n/a
Nylon Black	RAL 9011

Mechanical properties (*)

Injection molding

3D printing

	<u>Typical value</u>	<u>Test method</u>	<u>Typical value</u>	<u>Test method</u>
Tensile modulus	-	-	579.0 MPa	ISO 527 (1 mm/min)
Tensile stress at yield	-	-	27.8 MPa	ISO 527 (50 mm/min)
Tensile stress at break	-	-	34.4 MPa	ISO 527 (50 mm/min)
Elongation at yield	-	-	20.0 %	ISO 527 (50 mm/min)
Elongation at break	-	-	210.0 %	ISO 527 (50 mm/min)
Flexural strength	-	-	24.0 MPa	ISO 178
Flexural modulus	-	-	463.5 MPa	ISO 178
Izod impact strength, notched (at 23°C)	-	-	34.4 kJ/m ²	ISO 180
Charpy impact strength (at 23°C)	-	-	-	-
Hardness	-	-	-	-

Thermal properties

Typical value

Test method

Melt mass-flow rate (MFR)	6.2 g/10min	ISO 1133 (250 °C, 1.2 kg)
Heat deflection (HDT) at 0.455 MPa	-	-
Heat deflection (HDT) at 1.82 MPa	-	-
Glass transition	50 °C	-
Coefficient of thermal expansion (flow)	-	-
Coefficient of thermal expansion (xflow)	-	-
Melting temperature	185 - 195 °C	ISO 11357 (20 °C/min)
Thermal shrinkage	12 ± 2 %	DIN 53866 (100 °C, 30 min)

Other properties

Typical value

Test method

Specific gravity	1.14	-
Flame classification	-	-

(*) Seen notes.

Notes

Properties reported here are average of a typical batch. The 3D printed test specimens were printed in the XY plane, using the normal quality profile in Cura 2.1, an UM2+, a 0.4 mm nozzle, 90% infill, 250 °C nozzle temperature and 60 °C build plate temperature. The values are the average of 5 transparent and 5 black tensile bars. Ultimaker is constantly working on extending the TDS data.

Disclaimer

Any technical information or assistance provided herein is given and accepted at your risk, and neither the Ultimaker or its affiliates make any warranty relating to it or because of it. Neither Ultimaker nor its affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness of your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product; and nothing herein waives any of Ultimaker's conditions of sale. Specifications are subject to change without notice.

Version

Version 3.006

Date

28/02/2017

Ultimaker